



SALES SPECIFICATION SHEET  
**F200 GLY**  
 Granular Activated Carbon

Test	Specification		Calgon Carbon Test Method
	Min	Max	
IODINE NO., mg/g	850	-	TM-4 or ASTM D 4607
MOISTURE, wt%, as packed	-	2	TM-1 or ASTM D 2867
ABRASION NO.	75	-	TM-9
EFFECTIVE SIZE, mm	0.55	0.75	TM-47 or ASTM D 2862
UNIFORMITY COEFFICIENT	-	1.9	TM-47 or ASTM D 2862
ACID SOLUBLE IRON, wt%	-	0.40	TM-18
US SIEVE SERIES			TM-8
	+12	5	
	-40	4	

This activated carbon is certified to ANSI/NSF Standard 61

This product is Made to Stock

**Calgon Carbon Corporation's activated carbon products are continuously being improved and changes may have taken place since this publication went to press. (1965-01/24/97)**



Grupo Filtrantes

Av. Ejército Nacional 531 Col Granada Miguel Hidalgo

CDMX 11520 Tel. +52 55 1661-0684 Óp. 2

[ventas@filtrantes.com.mx](mailto:ventas@filtrantes.com.mx) [www.grupofiltrantes.com.mx](http://www.grupofiltrantes.com.mx)