

# OLC AW 12x40

## Coconut Acid Washed Activated Carbon

### Specification

Test	Min	Max	Calgon Carbon Test Method
IODINE NO., mg/g	1050	-	ASTM D 4607
MOISTURE, wt%, as packed	-	5	ASTM D 2867
A.D., g/cc	T&R	-	ASTM D 2854
ACID SOLUBLE ASH, wt%	-	1.0	ASTM D 6385
EXTRACTABLE pH	6	8	ASTM D 3838
HARDNESS NO.	97	-	ASTM D 3802
WATER EXTRACTABLE , wt%	-	1	ASTM D 5029
NSF 61, Pass/Fail	PASS	-	NSF 61,Note 3
US SIEVE SERIES			ASTM D 2862
> 12 US MESH	-	5	
16 US MESH	-	-	
20 US MESH	-	-	
30 US MESH	-	-	
40 US MESH	-	-	
< 40 US MESH	-	5	

**T&R = Test and Report**

**Note 3: This test is performed by CCC until the vendor has test capability and/or is certified.**