

Specification

Test	Min	Max	Calgon Carbon Test Method
IODINE NO., mg/g	1100	-	TM-4 or ASTM D 4607
ASH, wt%	-	5	TM-5
MOISTURE, wt%, as packed	-	2	TM-1 or ASTM D 2867
A.D. g/cc	0.50	-	TM-7 or ASTM D 2854
US SIEVE SERIES			TM-8
	+20	-	3
	-50	-	1